

CHEMTRONICS®

Technical Data Sheet

TDS # CW2610

CircuitWorks® Rubber Keypad Repair Kit

PRODUCT DESCRIPTION

CircuitWorks® Rubber Keypad Repair Kit permanently repairs rubber keypads by restoring conductivity to worn, intermittent, and nonconductive carbon contacts. This product easily returns rubber keypads to like-new condition. This system is flexible and very durable. The CircuitWorks® Rubber Keypad Repair Kit provides a silver/carbon coating that is effective and long lasting.

- Repairs nonconductive keypads
- Excellent electrical conductivity
- Wear-resistant coating
- Excellent adhesion
- System has 72 hour pot life
- Testing shows repairs can withstand over 500,000 simulated keystrokes

TYPICAL APPLICATIONS

CircuitWorks® Rubber Keypad Repair Kit is excellent for rework and repair applications including:

- Telephones
- Controllers
- Carbon Contact Keyboards
- Communication Equipment
- Miscellaneous Keypads

TYPICAL PRODUCT DATA AND PHYSICAL PROPERTIES

Composition

Material	Part A	Silver/Carbon/Rubber
	Part B	Hardener
Color	Part A	Dark Gray/Silver
	Part B	Amber Clear
Specific Gravity	Part A	2.5 - 2.7
	Part B	1.0

Cured Compound

Tack-Free Time @ 25°C (75°F)	1 Hour
Return to Service Time	24 Hours
Complete Cure @ 25°C(75°F)	72 Hours
Electrical Conductivity	Excellent
Durability	Excellent
Flexibility	Excellent

Shelflife 18 months

COMPATIBILITY

CircuitWorks® Rubber Keypad Repair Kit has excellent compatibility with most materials. As with any adhesive/sealant, compatibility with substrate should be determined on a non-critical area prior to use.

Read MSDS carefully prior to use.

Application: Paint the worn carbon contacts with the mixed conductive material using the enclosed applicator brushes.

Curing: At room temperature (<25°C), material dries tack-free in one hour. Repaired keypads can be returned to service in 24 hours. Ultimate properties are achieved in 72 hours. For faster drying, expose the material to approximately 190°F (90°C) for 10 minutes. DO NOT EXCEED 212°F (100°C).

Chemtronics® provides a technical hotline to answer your technical and application related questions. The toll free number is: **1-800-TECH-401.**

CW2605	1 set containing: 3g / 0.36 oz. Adhesive 0.33g / 0.01 oz. Curing Agent
CW2610	2 sets containing a total of: 10g / 0.36 oz. Adhesive 1.1g / 0.04 oz. Curing Agent

This information is believed to be accurate. It is intended for professional end users having the skills to evaluate and use the data properly. CHEMTRONICS® does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.

MANUFACTURED BY:
ITW CHEMTRONICS®
8125 COBB CENTER DRIVE
KENNESAW, GA 30152
1-770-424-4888

REV. D (03/01)

DISTRIBUTED BY:[illegible]